

Serial No. 09/ "CHEMICAL DERIVATIZATION OF SINGLE-WALL CARBON NANOTUBES TO FACILITATE SOLVATION THEREOF; AND USE OF DERIVATIZED NANOTUBES TO FORM CATALYST-CONTAINING SEED MATERIALS FOR USE IN MAKING CARBON FIBERS" to Margraves et al., (Attorney Docket No. 11321-P028US), filed concurrent to the date of this Application; and

Serial No. 09/ "CHEMICAL DERIVATIZATION OF SINGLE-WALL CARBON NANOTUBES TO FACILITATE SOLVATION THEREOF; AND USE OF DERIVATIZED NANOTUBES TO FORM CATALYST-CONTAINING SEED MATERIALS FOR USE IN MAKING CARBON FIBERS" to Margraves et al., (Attorney Docket No. 11321-P029US), filed concurrent to the date of this Application.

IN THE CLAIMS:

Please delete claims 1-51 without prejudice or disclaimer.

Please add new claims 52-96 listed below.

52. (New) A single wall carbon nanotube having one or more substituents covalently bonded to a sidewall of the single wall carbon nanotube.

53. (New) The single wall carbon nanotube of claim 52, wherein the substituents are selected from the group consisting of alkyl, acyl, aryl, aralkyl, halogen, substituted thiol, unsubstituted thiol, substituted amino, unsubstituted amino, hydroxy, and OR', wherein R' is selected from the group consisting of hydrogen, alkyl, acyl, aryl, aralkyl, halogen, substituted thiol, unsubstituted thiol, substituted amino, unsubstituted amino, a linear carbon chain, and a cyclic carbon chain.

54. (New) The single wall carbon nanotube of claim 53, wherein the linear carbon chain or the cyclic carbon chain or both is substituted with at least one heteroatom.

55. (New) The single wall carbon nanotube of claim 53, wherein the linear carbon chain or the cyclic carbon chain or both is substituted with one or more of the group consisting of =O, =S, hydroxy, an aminoalkyl, an amino acid, and a peptide of 2-8 amino acids.

1
2 56. (New) The single wall carbon nanotube of claim 52, wherein the substituents are
alkyl or phenyl.

1
2 57. (New) The single wall carbon nanotube of claim 52, further comprising metal
complexed to at least one of the substituents.

1
2 58. (New) The single wall carbon nanotube of claim 57, wherein the metal is selected
from the group consisting of Group VI B metals and Group VIII B metals.

1
2
3
4 59. (New) The single wall carbon nanotube of claim 52, wherein the amount of
substituent bonded to carbon atoms of the single wall carbon nanotube is at a substituent to carbon
ratio of from (a) one substituent to about 26 carbon atoms to (b) one substituent to about two carbon
atoms.

1
2
3
4 60. (New) The single wall carbon nanotube of claim 59, wherein the amount of
substituent bonded to the carbon atoms of the single wall carbon nanotube is at a substituent to
carbon ratio of from (a) one substituent to about ten carbon atoms to (b) one substituent to about two
carbon atoms.

1
2
3
4 61. (New) The single wall carbon nanotube of claim 60, wherein the amount of
substituent bonded to the carbon atoms of the single wall carbon nanotube is at the substituent to
carbon ratio of from (a) one substituent to about three carbon atoms to (b) one substituent to about
two carbon atoms.

1 62. (New) A product made by the process of covalently bonding substituents to carbon
2 atoms on a sidewall of the single wall carbon nanotube.

1 63. (New) The product of claim 62, wherein the substituents are selected from the group
2 consisting of alkyl, acyl, aryl, aralkyl, halogen, substituted thiol, unsubstituted thiol, substituted
3 amino, unsubstituted amino, hydroxy, and OR', wherein R' is selected from the group consisting of
4 hydrogen, alkyl, acyl, aryl, aralkyl, halogen, substituted thiol, unsubstituted thiol, substituted amino,
5 unsubstituted amino, a linear carbon chain, and a cyclic carbon chain.

1 64. (New) The product of claim 63, wherein the linear carbon chain or the cyclic carbon
2 chain or both is substituted with at least one heteroatom.

1 65. (New) The product of claim 63, wherein the linear carbon chain or the cyclic carbon
2 chain or both is substituted with one or more of the group consisting of =O, =S, hydroxy, an
3 aminoalkyl, an amino acid, and a peptide of 2-8 amino acids.

1 66. (New) The product of claim 62, wherein the substituents are selected from the group
2 consisting of fluorine, alkyl and phenyl.

1 67. (New) The product of claim 62, further comprising the step of complexing a metal
2 to at least one of the substituents.

1 68. (New) The product of claim 67, wherein the metal is selected from the group
2 consisting of Group VIB metals and Group VIII B metals.

1 69. (New) The product of claim 62, wherein the amount of substituent bonded to carbon
2 atoms of the single wall carbon nanotube is at a substituent to carbon ratio of from (a) one
3 substituent to about 26 carbon atoms to (b) one substituent to about two carbon atoms.

1 70. (New) The product of claim 69, wherein the amount of substituent bonded to the
2 carbon atoms of the single wall carbon nanotube is at the substituent to carbon ratio of from (a) one
3 substituent to about ten carbon atoms to (b) one substituent to about two carbon atoms.

1 71. (New) The product of claim 70, wherein the amount of substituent bonded to the
2 carbon atoms of the single wall carbon nanotube is at the substituent to carbon ratio of from (a) one
3 substituent to about three carbon atoms to (b) one substituent to about two carbon atoms.

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
289
290
291
292
293
294
295
296
297
298
299
299
300
301
302
303
304
305
306
307
308
309
309
310
311
312
313
314
315
316
317
318
319
319
320
321
322
323
324
325
326
327
328
329
329
330
331
332
333
334
335
336
337
338
339
339
340
341
342
343
344
345
346
347
348
349
349
350
351
352
353
354
355
356
357
358
359
359
360
361
362
363
364
365
366
367
368
369
369
370
371
372
373
374
375
376
377
378
379
379
380
381
382
383
384
385
386
387
388
389
389
390
391
392
393
394
395
396
397
398
399
399
400
401
402
403
404
405
406
407
408
409
409
410
411
412
413
414
415
416
417
418
419
419
420
421
422
423
424
425
426
427
428
429
429
430
431
432
433
434
435
436
437
438
439
439
440
441
442
443
444
445
446
447
448
449
449
450
451
452
453
454
455
456
457
458
459
459
460
461
462
463
464
465
466
467
468
469
469
470
471
472
473
474
475
476
477
478
479
479
480
481
482
483
484
485
486
487
488
489
489
490
491
492
493
494
495
496
497
498
499
499
500
501
502
503
504
505
506
507
508
509
509
510
511
512
513
514
515
516
517
518
519
519
520
521
522
523
524
525
526
527
528
529
529
530
531
532
533
534
535
536
537
538
539
539
540
541
542
543
544
545
546
547
548
549
549
550
551
552
553
554
555
556
557
558
559
559
560
561
562
563
564
565
566
567
568
569
569
570
571
572
573
574
575
576
577
578
579
579
580
581
582
583
584
585
586
587
588
589
589
590
591
592
593
594
595
596
597
598
599
599
600
601
602
603
604
605
606
607
608
609
609
610
611
612
613
614
615
616
617
618
619
619
620
621
622
623
624
625
626
627
628
629
629
630
631
632
633
634
635
636
637
638
639
639
640
641
642
643
644
645
646
647
648
649
649
650
651
652
653
654
655
656
657
658
659
659
660
661
662
663
664
665
666
667
668
669
669
670
671
672
673
674
675
676
677
678
679
679
680
681
682
683
684
685
686
687
688
689
689
690
691
692
693
694
695
696
697
698
698
699
699
700
701
702
703
704
705
706
707
708
709
709
710
711
712
713
714
715
716
717
718
719
719
720
721
722
723
724
725
726
727
728
729
729
730
731
732
733
734
735
736
737
738
739
739
740
741
742
743
744
745
746
747
748
749
749
750
751
752
753
754
755
756
757
758
759
759
760
761
762
763
764
765
766
767
768
769
769
770
771
772
773
774
775
776
777
778
779
779
780
781
782
783
784
785
786
787
788
789
789
790
791
792
793
794
795
796
797
798
798
799
799
800
801
802
803
804
805
806
807
808
809
809
810
811
812
813
814
815
816
817
818
819
819
820
821
822
823
824
825
826
827
828
829
829
830
831
832
833
834
835
836
837
838
839
839
840
841
842
843
844
845
846
847
848
849
849
850
851
852
853
854
855
856
857
858
859
859
860
861
862
863
864
865
866
867
868
869
869
870
871
872
873
874
875
876
877
878
879
879
880
881
882
883
884
885
886
887
888
889
889
890
891
892
893
894
895
896
897
898
898
899
899
900
901
902
903
904
905
906
907
908
909
909
910
911
912
913
914
915
916
917
918
919
919
920
921
922
923
924
925
926
927
928
929
929
930
931
932
933
934
935
936
937
938
939
939
940
941
942
943
944
945
946
947
948
949
949
950
951
952
953
954
955
956
957
958
959
959
960
961
962
963
964
965
966
967
968
969
969
970
971
972
973
974
975
976
977
978
979
979
980
981
982
983
984
985
986
987
988
989
989
990
991
992
993
994
995
996
997
998
998
999
999
1000

1 72. (New) A product made by the process comprising:

2 (a) fluorinating a single wall carbon nanotube;

3 (b) reacting the fluorinated single wall carbon nanotube with a compound containing
4 a substituent to covalently bond the substituents to the single wall carbon nanotube.

1 73. (New) The product of claim 72, wherein the substituents are selected from the group
2 consisting of alkyl, acyl, aryl, aralkyl, halogen, substituted thiol, unsubstituted thiol, substituted
3 amino, unsubstituted amino, hydroxy, and OR', a linear carbon chain, a cyclic carbon chain, and
4 peptide, wherein R' is selected from the group consisting of hydrogen, alkyl, acyl, aryl, aralkyl,
5 halogen, substituted thiol, unsubstituted thiol, substituted amino, unsubstituted amino, a linear
6 carbon chain, and a cyclic carbon chain.

1 74. (New) The product of claim 73, wherein the linear carbon chain or the cyclic carbon
2 chain or both is substituted with at least one heteroatom.

1 75. (New) The product of claim 73, wherein the linear carbon chain or the cyclic carbon
2 chain or both is substituted with one or more of the group consisting of =O, =S, hydroxy, an
3 aminoalkyl, an amino acid, and a peptide of 2-8 amino acids.

1 76. (New) The product of claim 72, wherein the substituents are alkyl or phenyl.

1 77. (New) The product of claim 72 made by the process further comprising the step of
2 complexing a metal to at least one of the substituents.

1 78. (New) The product of claim 77, wherein the metal is selected from the group
2 consisting of Group VI B metals and Group VIII B metals.

1 79. (New) The product of claim 72, wherein the amount of substituent bonded to carbon
2 atoms of the single wall carbon nanotube is at a substituent to carbon ratio of from (a) one
3 substituent to about 26 carbon atoms to (b) one substituent to about two carbon atoms.

1 80. (New) The product of claim 79, wherein the amount of substituent bonded to the
2 carbon atoms of the single wall carbon nanotube is at the substituent to carbon ratio of from (a) one
3 substituent to about ten carbon atoms to (b) one substituent to about two carbon atoms.

1 81. (New) The product of claim 80, wherein the amount of substituent bonded to the
2 carbon atoms of the single wall carbon nanotube is at the substituent to carbon ratio of from (a) one
3 substituent to about three carbon atoms to (b) one substituent to about two carbon atoms.

1 82. (New) The product of claim 72, wherein said step of fluorinating the single wall
2 carbon nanotube comprises exposing the single wall carbon nanotube to a fluorinating agent.

1 83. (New) The product of claim 82, wherein the fluorinating agent is selected from the
2 group consisting of fluorine, CIF₃, BrF₃, IF₅, XeF₂, XeF₄, AgF₂, and MnF₃.

1 84. (New) The product of claim 82, wherein the fluorinating step occurs at a reaction
2 temperature up to about 500°C.

1 85. (New) The product of claim 82, wherein the reaction temperature is between about
2 250°C and about 400°C.

1 86. (New) A derivatized single wall carbon nanotube made by the process comprising the
2 steps of:

3 (a) reacting the single wall carbon nanotube with a fluorinating agent;

4 (b) solvating the single wall carbon nanotube from step (i); and

5 (c) reacting the fluorinated single wall carbon nanotube with a compound containing
6 a substituent to covalently bond the substituent to the single wall carbon nanotube.

1 87. (New) The derivatized single wall carbon nanotube of claim 86, wherein the
2 substituents are selected from the group consisting of alkyl, acyl, aryl, aralkyl, halogen, substituted
3 thiol, unsubstituted thiol, substituted amino, unsubstituted amino, hydroxy, and OR', wherein R' is
4 selected from the group consisting of hydrogen, alkyl, acyl, aryl, aralkyl, halogen, substituted thiol,
5 unsubstituted thiol, substituted amino, unsubstituted amino, a linear carbon chain, and a cyclic
6 carbon chain.

1 88. (New) The derivatized single wall carbon nanotube of claim 87, wherein the linear
2 carbon chain or the cyclic carbon chain or both is substituted with at least one heteroatom.

1 89. (New) The derivatized single wall carbon nanotube of claim 87, wherein the linear
2 carbon chain or the cyclic carbon chain or both is substituted with one or more of the group
3 consisting of =O, =S, hydroxy, an aminoalkyl, an amino acid, and a peptide of 2-8 amino acids.

1 90. (New) The derivatized single wall carbon nanotube of claim 86, wherein the
2 fluorinating agent is selected from the group consisting of fluorine, ClF₃, BrF₃, IF₅, XeF₂, XeF₄,
3 AgF₂, and MnF₃.

1 91. (New) The derivatized single wall carbon nanotube of claim 86, wherein the solvation
2 step comprises sonication.

1 92. (New) The derivatized single wall carbon nanotube of claim 86, wherein the solvation
2 step comprises using a solvent selected from the group consisting of an alcohol, CHCl₃, and
3 dimethylformamide.

1 93. (New) The derivatized single wall carbon nanotubes of claim 92, wherein the alcohol
2 is selected from the group consisting of methanol, ethanol, 2,2,2-trifluoroethanol, 2-propanol,
3 2-butanol, n-pentanol, n-hexanol, cyclohexanol and n-heptanol.

1 94. (New) The derivatized single wall carbon nanotube of claim 86, wherein the amount
2 of substituent bonded to carbon atoms of the single wall carbon nanotube is at a substituent to carbon
3 ratio of from (a) one substituent to about 26 carbon atoms to (b) one substituent to about two carbon
4 atoms.

1 95. (New) The derivatized single wall carbon nanotube of claim 94, wherein the amount
2 of substituent bonded to the carbon atoms of the single wall carbon nanotube is at a substituent to
3 carbon ratio of from (a) one substituent to about ten carbon atoms to (b) one substituent to about two
4 carbon atoms.

1 96. (New) The derivatized single wall carbon nanotube of claim 95, wherein the amount
2 of substituent bonded to the carbon atoms of the single wall carbon nanotube is at the substituent to
3 carbon ratio of from (a) one substituent to about three carbon atoms to (b) one substituent to about
4 two carbon atoms.